APPENDIX N. SPECIALTY COATINGS VOC CONTENT LIMITS [REVOKED]

The following table is for use only in OAC 252:100-39-47.

| Coating Type | Limit | |
|--|--------|------------------|
| | lb/gal | g/l ¹ |
| Ablative Coating | 5.0 | 600 |
| Adhesion Promoter | 7.4 | 890 |
| Adhesive Bonding Primers: | | |
| Cured at 250°F or below | 7.1 | 850 |
| Cured above 250°F | 8.6 | 1,030 |
| Adhesives: | | |
| Commercial Interior Adhesive | 6.3 | 760 |
| Cyanoacrylate Adhesive | 8.5 | 1,020 |
| Fuel Tank Adhesive | 5.2 | 620 |
| Nonstructural Adhesive | 3.0 | 360 |
| Rocket Motor Bonding Adhesive | 7.4 | 890 |
| Rubber-based Adhesive | 7.1 | 850 |
| Structural Autoclavable Adhesive | 0.5 | 60 |
| Structural Nonautoclavable Adhesive | 7.1 | 850 |
| Antichafe Coating | 5.5 | 660 |
| Bearing Coating | 5.2 | 620 |
| Caulking and Smoothing Compounds | 7.1 | 850 |
| Chemical Agent-Resistant Coating | 4.6 | 550 |
| Clear Coating | 6.0 | 720 |
| Commercial Exterior Aerodynamic Structure Primer | 5.4 | 650 |
| Compatible Substrate Primer | 6.5 | 780 |
| Corrosion Prevention Compound | 5.9 | 710 |

SPECIALTY COATINGS VOC CONTENT LIMITS

| Coating Type | Limit | |
|--|--------|---------|
| | lb/gal | g/l^1 |
| Cryogenic Flexible Primer | 5.4 | 645 |
| Cryoprotective Coating | 5.0 | 600 |
| Dry Lubricative Material | 7.3 | 880 |
| Electric or Radiation-Effect Coating | 6.7 | 800 |
| Electrostatic Discharge and Electromagnetic Interference (EMI) Coating | 6.7 | 800 |
| Elevated-Temperature Skydrol-Resistant Commercial Primer | 6.2 | 740 |
| Epoxy Polyamide Topcoat | 5.5 | 660 |
| Fire-Resistant (Interior) Coating | 7.3 | 800 |
| Flexible Primer | 5.3 | 640 |
| Flight-Test Coatings | | |
| Missile or Single Use Aircraft | 3.5 | 420 |
| All Other | 7.0 | 840 |
| Fuel Tank Coating | 6.0 | 720 |
| High-Temperature Coating | 7.1 | 850 |
| High-Temperature Radiation-Effect Coating | 8.5 | 1,020 |
| Insulation Covering | 6.2 | 740 |
| Intermediate Release Coating | 6.4 | 750 |
| Lacquer | 6.9 | 830 |
| Maskants: | | |
| Bonding Maskant | 10.02 | 1,230 |
| Critical Use and Line Sealer Maskant | 8.5 | 1,020 |
| Seal Coat Maskant | 10.2 | 1,230 |
| Metallized Epoxy Coating | 6.2 | 740 |
| Mold Release | 6.5 | 780 |
| Optical Anti-Reflective Coating | 6.3 | 750 |
| Part Marking Coating | 7.1 | 850 |

| Coating Type | Limit | |
|---------------------------------------|--------|------------------|
| | lb/gal | g/l ¹ |
| Pretreatment Coating | 6.5 | 780 |
| Rain Erosion-Resistant Coating | 7.1 | 850 |
| Rocket Motor Nozzle Coating | 5.5 | 660 |
| Scale Inhibitor | 7.3 | 880 |
| Screen Print Ink | 7.0 | 840 |
| Sealants: | | |
| Extrudable/Rollable/Brushable Sealant | 2.3 | 280 |
| Sprayable Sealant | 5.0 | 600 |
| Silicone Insullation Material | 7.1 | 850 |
| Solid Film Lubricant | 7.3 | 880 |
| Specialized Function Coating | 7.4 | 890 |
| Temporary Protective Coating | 2.7 | 320 |
| Thermal Control Coating | 6.7 | 800 |
| Wet Fastener Installation Coating | 5.6 | 675 |
| Wing Coating | 7.1 | 850 |

¹Coating limits expressed in terms of mass (grams) of VOC per volume (liters) of coating less water and less exempt solvent using Equation 1 below.

EQUATION 1

Grams of VOC per liter of coating (less water and less exempt solvent) shall be calculated using the following formula:

 $g/l = (W_s - W_w - W_{es})/(V_s - V_w - V_{es})$

Where:

$$\begin{split} W_s &= \text{weight of total volatiles in grams} \\ W_w &= \text{weight of water in grams} \\ W_{es} &= \text{weight of exempt compounds in grams} \\ V_s &= \text{volume of coating in liters} \\ V_w &= \text{volume of water in liters} \\ V_{es} &= \text{volume of exempt compounds in liters} \end{split}$$